

CiCC is a light cured dental composite in a blister intended for one patient only, suitable for all fillings and restorations of cavities and defects in anterior, posterior, deciduous and permanent teeth of both caries and non-caries aetiology.

INDICATIONS FOR USE

- Black's class I, II, III, IV and V cavities
- dental splints, permanent – external or internal layer
- dental splints, temporary – external layer
- composite and acrylic prosthetic restoration repairs

INSTRUCTIONS FOR USE

1. Prepare the cavity in the normal way.
2. Etch using ETCHGEL, rinse and dry gently.
3. Apply a thin layer of a bonding system. CiCC can be used with any standard, light cured, dimethacrylate resin-based bonding systems. A bonding system should be applied in accordance with the manufacturer's instructions.
4. In the case of very deep cavities, use a cavity liner (e.g. glass ionomer cement)
5. Peel back the aluminium foil and open the blister.
6. Load your instrument with the composite.
7. Fill the cavity, light curing each layer in accordance with the polymerisation table provided.
8. Adjust to the bite and polish.

CiCC is a polymer dental material type 1 (class 2, group 1), which meets the requirements of the ISO 4049 standard. CiCC composite undergoes free radical polymerisation activated by visible light from the blue region (400-500 nm).

CiCC has a radio-opacity equivalent to approx. 5 mm of aluminium (aluminium has a radio-opacity equivalent to that of dentine; thus 1 mm of material having a radio-opacity equivalent to 1 mm of aluminium has a radio-opacity equivalent to that of dentine and 2 mm of aluminium is equivalent to enamel).

If necessary, choose the right shade from the CiCC composite shade guide before starting the treatment when the tooth is naturally moisturised.

COMPOSITION

CiCC is composed of dimethacrylate resins. Mineral fillers make up about 78% by weight of the composite.

POLYMERISATION TABLE

Lamp	Shade	20 s	30 s
Halogen/LED (500-800 mW/cm ²)	A1, A2, A3, B1, B2, C2, D2	2.0 mm	2.5 mm
	A3.5, 0A2, 0A3, D3	1.8 mm	2.2 mm
	INCISAL	3.0 mm	3.5 mm
	PINK, BLUE		1.5 mm
LED (>800 mW/cm ²)	A1, A2, A3, B1, B2, C2, D2	2.5 mm	3.0 mm
	A3.5, 0A2, 0A3, D3	2.2 mm	2.5 mm
	INCISAL	>35 mm	>35 mm
	PINK, BLUE		2.0 mm

MD Medical device class IIa**COMPOSITION**

Mixture of dimethacrylate resins: BisGMA, TEGDMA, UDMA, BisEMA; mineral fillers (about 78 wt%): Al-Ba-B-Si glass, fumed silica, pigments; photoinitiator (CQ : DMAEMA). The size of inorganic filler particles is between 20 nm and 2.0 µm.

CONTRAINDICATIONS

Do not use CiCC composite in patients with a known allergy to any of the components.

ADVERSE REACTIONS

None known. However, an allergic reaction cannot be excluded in particularly sensitive individuals. In case of an immediate allergic reaction, stop using the product. In case of a delayed allergic reaction, remove the restoration.

LIMITATIONS IN USAGE, INTERACTIONS

Do not use if it is impossible to completely isolate the area from saliva, blood or moisture. Contamination may disrupt the polymerisation process, affecting the mechanical properties of the composite and decreasing the durability of the restoration, which in turn may result in secondary caries formation.

Do not use with materials containing phenolic compounds, especially eugenol and thymol. Such materials may disrupt polymerisation of the composite.

PRECAUTIONS

Avoid contact of unpolymerised product with skin, eyes and the soft tissues of the mouth. In case of such contact, rinse with plenty of water. In case of any symptoms, consult a doctor giving information about the product. To minimise the risk of contact, always wear personal protective equipment such as gloves, face masks and safety glasses.

In case of swallowing or aspiration into the respiratory tract, seek immediate medical attention.

To isolate the operative field and to protect the patient, the use of a rubber dam is recommended.

Ensure sufficient polymerisation of the entire composite layer, especially in places which are difficult to access. Insufficiently polymerised product can be allergenic.

In case of any contamination of an unpolymerised composite, the contaminated material layer must be removed. In case of contamination or mechanical damage to an already polymerised layer, gently etch its surface and cover it with a bonding system. Cure in accordance with the polymerisation table provided.

In case of insufficient polymerisation, remove the incorrectly polymerised layer and apply another one, curing it correctly.

Protect the blisters against mechanical damage. Do not use if the aluminium foil is damaged.

WARNINGS

Keep out of reach of children and unauthorised persons. Protect from light. Polymerisation of the composite may be initiated by ambient light or by a dental operating lamp. Protect from heat. Do not freeze. Use in accordance with the manufacturer's instructions. Do not use after the expiry date.

STORAGE

Store at a temperature under 25°C. Do not expose to direct sunlight. If stored at a lower temperature, bring back to room temperature before use. For use by dentists and dental technicians only.

WARRANTY

ARKONA will replace products that have been proved to be defective or will refund the price of purchase. ARKONA is not liable for any loss or damage caused by misuse or improper use of the product.

Instruction for use issued on 22.03.2021

**ARKONA**

Laboratorium Farmakologii Stomatologicznej
Nasutów 99 C, 21-025 Niemce, EU

